

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 05-093120

(43)Date of publication of application : 16.04.1993

(51) Int. Cl. C08L 25/08
C08K 3/20
C08L 25/08
C08L 25/08
C08L 25/08
C08L 51/00
C08L 51/04
C08L 51/08
C08L 63/00
C08L 63/00
C08L 81/00
C08L 83/04
//C08L 25/08
C08L 63:00
C08L 51:00
C08L 81:00)

(21)Application number : 03-255388 (71)Applicant : SHOWA DENKO KK
(22)Date of filing : 02.10.1991 (72)Inventor : MAEDA HIROYUKI
MACHIDA MITSUNOBU
NAKAMURA TERUO
AOYAMA TSUTOMU
WASHIYAMA JUNICHIRO

(54) RESIN COMPOSITION

(57) Abstract:

PURPOSE: To prepare a resin compsn. excellent in heat resistance, impact strength, flame retardance, and moldability by compounding a heat-resistant resin, a thermoplastic resin, antimony oxide, a brominated epoxy compd., specific reaction products, and a silicone oil.

CONSTITUTION: 100 pts.wt. resin component comprising a heat-resistant resin selected from the group consisting of a styrenic compd.-imide compd. copolymer and a rubber-reinforced copolymer and a thermoplastic resin selected from the group consisting of a copolymer obtd. by grafting styrene and methyl methacrylate onto a rubber component, an AS resin, and an MS resin is compounded with 0.5-10 pts.wt. antimony oxide, 5.0-40 pts.wt. the sum of a brominated epoxy compd., a brominated epoxy compd. having both molecular terminals reacted with 2,4,6-tribromophenol, and an acrylonitrile-butadiene copolymer having both molecular terminals carboxylated, and 0.1-3.0 pts.wt. silicone oil.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's
decision of rejection][Kind of final disposal of application
other than the examiner's decision of
rejection or application converted
registration]

BEST AVAILABLE COPY